

Toughening Limitation – Guidelines

Figure 1

Maximum hole diameter to be less than 50% of narrowest height/width of glass for holes over 75mm. Dog and cat doors attract special rules




Figure 3

Holes at corners distance to be 4 x thickness of glass from one edge and at least 1.5 x thickness from other edge. Except where – glass thickness > 10mm to be 4 x thickness to both edges and where – angle of corner < 90° to be 4 x thickness to both edges

Figure 1

Height/width of cut-out to be no more than 33% of height/width of glass

